

2K ELASTOMERIC CEMENTITIOUS WATERPROOF HIGHLY FLEXIBLE COATING FOR CONCRETE & MASONRY

Description

ELASTOCEM FLEX is an elastomeric flexible, two component polymers modified cementitious system that requires only onsite mixing forming ideal waterproof coating on concrete, masonry, and most other construction materials. ELASTOCEM FLEX can simply be applied by stiff brush, roller or trowel to obtain the desired thickness.

ELASTOCEM FLEX will bridge an existing crack of up to 0.5 mm in width, or up to 2mm when reinforced with 100% virgin polypropylene woven fabric.

Uses

ELASTOCEM FLEX is a high performance elastomeric cementitious coating used for waterproofing and to protect atmospherically exposed reinforced concrete structures from attack by acid gases, chloride ions, oxygen & water. ELASTOCEM FLEX is suitable for all types of structures like,

- Water-retaining structures subjected to movements
- Basement-waterproofing
- To protect concrete from water, carbonation and de-icing salts.
- Waterproofing of roofs, sunken floors in bathrooms, Swimming Pools, Drainage culverts, Kitchens, Shower rooms, WC, etc.
- Waterproofing coating for drinking water tanks, sumps, etc.
- Foundations in contact with ground water under saline conditions

Advantages

- Withstands high positive and negative hydrostatic pressures
- Waterproof-suitable for water retaining structures. Allows water vapour to escape from the structure.
- Excellent barrier to carbon dioxide, chloride and sulphate ions.
- High resistance to the effect of long-term weathering, durable in all climate conditions including UV attack.
- Nontoxic - ideal for potable water tanks.
- Flexible, with thermal expansion similar to concrete.
- Excellent bond to concrete and masonry
- Bonds to green or damp concrete.
- Good crack accommodation capacity.
- Minimum surface preparation needed and low labour costs.

Standard Compliance

BS 6920: 2000 Effect on Water Quality.
DIN 1048: Water Penetration Test.
BS EN 13501-1 classification.

Characteristic

Mixing Ratio, by weight	: 2 (powder):1(liquid)
Pot Life	: 45 Minutes at 25°C
Recoatable	: 6 - 8 Hours
% Elongation	: $\geq 120\%$
Tensile strength	: ≥ 1.5 kg/cm ²
Resistance to water penetration at 0.2 kgf/cm ² for 6 hours	No penetration
Static crack accommodation	Up to 2mm
Adhesion strength, N/mm ² (ASTM D 4541)	>1

Direction of use

Surface preparation

The surface to be coated must be clean and sound. Remove all traces of formwork, release agents, previous coatings, laitance and any other contaminants that may affect the bond adversely. Suitable cleaning methods include high pressure water jetting and grit blasting. Mechanical wire brushing may be appropriate for small areas. After the above surface preparation, surfaces must be thoroughly washed with clean potable water to remove all dust and loose particles. Spalled surfaces or those containing large blow holes, cracks and other such defects should be repaired using REPCON FC concrete repair mortars. For further advice on suitable repair mortars, contact our local representative.

Mixing

ELASTOCEM FLEX is supplied in premeasured units and should be mixed on site utilizing clean containers. Slowly add the powder to the liquid and mix, using a slow speed drill fitted with a suitable paddle. Leave the mixed material to stand for 5 minutes to allow for full saturation to take place. Remix to restore the consistency. Do not mix more material than can be used in half an hour.

Application

Always apply ELASTOCEM FLEX to pre-dampened surface. High-suction substrates require more dampening than dense substrates. However, make sure there is no free-standing water. Apply by brush or broom. Mixed material must be used within 30 to 45 minutes, or less under hot weather conditions.

2K ELASTOMERIC CEMENTITIOUS WATERPROOF HIGHLY FLEXIBLE COATING FOR CONCRETE & MASONRY

First Coat: Brush or broom the mix firmly onto the pre-dampened, prepared surface. Care must be taken not to spread the material too thinly. When the material begins to drag or “ball”, do not add more liquid/water but dampen the surface again.

Second Coat: Allow at least overnight to cure before applying subsequent coats. Dampen the first coat and remove excess moisture. Brush or broom the mix onto the surface (as above) finishing in the opposite direction to the first coat.

With reinforcing mesh: 100% virgin polypropylene woven mesh is used to reinforce ELASTOCEM FLEX. Embed the mesh in thick base layer of approximately 0.5 mm thickness, covered with the first coat of ELASTOCEM FLEX while base coat is still wet. Ensure that the mesh is a minimum of 200 mm wide when treating existing cracks, joints, junctions.

Curing

Under hot or excessive drying conditions fog-spray after the initial set has taken place for as long as practicable. In cold, humid or unventilated areas it may be necessary to leave the application for a longer time curing period or to introduce forced air movement. Never use dehumidifiers during curing periods.

Coverage

Each square metre will require minimum of 0.65 Kg of mixed material per layer. The coverage rate for each layer will be strongly influenced by the roughness of the substrate.

1.3 kg / m² in two coats to achieve 1 mm thickness.
2.6 kg / m² in three coats to achieve 2 mm thickness.
Depending on surface condition the value may be differed.

Equipment cleaning

Not hardened material may simply be removed with water.

Packaging

ELASTOCEM FLEX is available in 3kg & 15kg pack.

Storage and Shelf life

ELASTOCEM FLEX should be stored above freezing temperatures. Store under cover, out of direct sunlight and protect from extremes of temperature. In tropical climates the product must be stored in an air-conditioned environment.

Shelf Life: Shelf life of the powder is 12 months and liquid is 12 months when stored as recommended. Depending on storage conditions, the shelf life may be greater than stated. Please contact our local representative regarding suitability for use and dosage recommendations if the shelf life of ELASTOCEM FLEX has been exceeded.

Safety precautions

ELASTOCEM FLEX does not fall into the hazard classifications. However, it should not be swallowed or allowed to come into contact with the skin and eyes.

Suitable protective gloves and goggles should be worn. Splashes on the skin should be removed with water. In case of contact with the eyes it shall be rinsed immediately with plenty of water and medical advice sought immediately. If swallowed, medical attention shall be sought immediately - Vomiting should not be induced.

Note

All Technical Data Sheets of FIRSTCHOICE SPECIALITY CHEMICALS are updated on regular basis; it is the user's responsibility, to obtain the most recent issue. Field services where provided, does not constitute supervisory responsibility, for additional information contact our local representative.

Disclaimer

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labor involved in the application are beyond our control.